

Issue Date: 01-01-2015  
Revision Date: 02-16-2026  
Renewal Date: 02-28-2027

**DIVISION: 07 00 00 – THERMAL AND MOISTURE PROTECTION**  
**Section: 07 21 00 – Thermal Insulation**  
**Section: 07 21 19 – Foamed-in-Place Insulation**  
**Section: 07 25 00 – Water-resistive Barriers/Weather Barriers**

**REPORT HOLDER:**  
**BASF Corporation**  
**1703 Crosspoint Avenue**  
**Houston, Texas 77054**  
**(888) 900-FOAM**  
[www.spf.basf.com](http://www.spf.basf.com)

**REPORT SUBJECT:**  
**SPRAYTITE® (SP, 158, and 178); and WALLTITE® US Spray-applied Polyurethane Foam Insulations**

### 1.0 SCOPE OF EVALUATION

This Research Report addresses compliance with the following Codes:

- 2024, 2021, 2018 *International Building Code®* (IBC)
- 2024, 2021, 2018 *International Residential Code®* (IRC)
- 2024, 2021, 2018 *International Energy Conservation Code®* (IECC)

The insulations described in this report have been evaluated for the following properties:

- Physical properties
- Surface-burning characteristics
- Thermal resistance
- Air permeability
- Vapor permeance
- Alternative to water-resistive barriers
- Alternatives to thermal barriers
- Alternatives to ignition barriers
- Use in fire-resistance-rated construction
- Use in Types I, II, III, and IV construction
- Use in Type V construction

See Table 1 for applicable Code sections related to these properties.

NOTE: This report references the most recent code edition cited. Section numbers may be different for earlier editions of the codes.

### 2.0 USES

SPRAYTITE® (SP, 158, and 178) and WALLTITE® US insulations are nonstructural thermal insulating materials for use on interior and exterior walls, floors, and roofs.

The insulations may be used as air-impermeable insulation as described in Section 3.2.3.

The insulations may be used as a vapor retarder as described in Section 3.2.5.

The insulations may be used in any Type of construction. When used in exterior walls in Types I, II, III, and IV construction (under the IBC), the wall construction must be in accordance with Section 4.7 and, as applicable, Section 4.6.

When installed as described in Section 4.5, the SPRAYTITE® 178 and WALLTITE® US may be used as an alternative to the water-resistive barrier required in IBC Section 1403.2 and IRC Section R703.2.

The insulations may be used in fire-resistance-rated construction when construction is as described in Section 4.6.

### 3.0 DESCRIPTION

#### 3.1 Materials:

**3.1.1 Insulation:** SPRAYTITE® (SP, 158, and 178) and WALLTITE® US are two-component, closed-cell, rigid foam plastic insulations. The insulations are produced the field by professional insulation contractors combining an isocyanate component "A" with a resin component "B", resulting in products having a nominal density of 2.0 pcf. SPRAYTITE® and WALLTITE®



insulations use an A component designated as ELASTOSPRAY® 8000A. Each insulation uses a proprietary blend for the B component. The B components have a shelf life of six months, and the A component has a shelf life of twelve months, when stored in factory-sealed containers at temperatures between 50°F and 80°F.

### 3.1.2 Intumescent Coatings:

**3.1.2.1 Aldocoat® 800 Intumescent Coating:** Aldocoat® 800 intumescent coating, manufactured by Aldo Products Company, is a single-component, water-based latex coating supplied in 5-gallon pails and 55-gallon drums. The materials have a shelf-life of six months when stored in a factory-sealed container at temperatures of 40°F and 90°F.

**3.1.2.2 NoBurn® Plus ThB Intumescent Coating:** No-Burn® Plus ThB is a one-part water-based intumescent coating manufactured by No-Burn, Inc. The coating is supplied in 5-gallon pails and 55-gallon drums and has a shelf life of 18 months when stored in unopened containers between 40°F and 90°F. No-Burn® Plus ThB complies with ICC-ES AC456 as recognized in IAPMO Uniform Evaluation Service Report ER-0305.

**3.1.2.3 No-Burn® Plus Intumescent Coating:** No-Burn® Plus is a one-part water based intumescent coating manufactured by No-Burn, Inc. The Coating is in 5-gallon pails and 55-gallon drums and has a shelf life of three years when stored in unopened containers between 40°F and 90°F. No-Burn® Plus is recognized in IAPMO Uniform Evaluation Service Report ER-0305.

**3.1.2.4 No-Burn® Plus XD Intumescent Coating:** No-Burn® Plus XD is a one-part water-based intumescent coating manufactured by No-Burn, Inc. The coating is supplied in 5-gallon pails and 55-gallon drums and has a shelf life of three years when stored in unopened containers between 40°F and 90°F. No-Burn® Plus XD is recognized in IAPMO Uniform Evaluation Service Report ER-0305.

**3.1.2.5 FIRESHELL® (F10E) Coating:** FIRESHELL® (F10E) intumescent coating is a proprietary, water-based, one-part, nonflammable coating manufactured by ICP Construction. The coating is supplied in 5-gallon pails and 55-gallon drums and has a shelf life of twelve months when stored in factory-sealed containers at

temperatures between 45°F and 75°F. F10E complies with ICC-ES AC456 as recognized in ICC-ES ESR-3997.

**3.1.2.6 FIRESHELL® (IB-4) Coating:** FIRESHELL® (IB-4) intumescent coating is a proprietary, water-based, one-part, nonflammable coating manufactured by ICP Construction. The coating is supplied in 5-gallon pails and 55-gallon drums and has a shelf life of twelve months when stored in factory-sealed containers at temperatures between 45°F and 75°F.

**3.1.2.7 Flame Seal® TB Intumescent Coating:** Flame Seal TB intumescent coating, manufactured by Flame Seal Products, Inc., is a two-component, four-to-one by-volume, liquid-applied, water-based polymeric intumescent coating. The coating is supplied in 6-gallon pails and 55-gallon drums and has a shelf-life of six months when stored in factory-sealed containers at temperatures between 40°F and 90°F. When applied at a minimum thickness of 25 mils wet film over SPRAYTITE® (SP, 158, and 178), and WALLTITE® US insulations, the assembly has a flame spread index of 25 or less and a smoke-developed index of 450 or less, when tested in accordance with ASTM E84.

**3.1.2.8 DC315 Intumescent Coating:** DC315 intumescent coating, manufactured by International Fireproof Technology, Inc., is a water-based coating supplied in 5-gallon pails and 55-gallon drums and has a shelf life of two years when stored in factory-sealed containers at temperatures between 41°F and 95°F. DC315 complies with ICC-ES AC456 as recognized in IAPMO ER-0499.

**3.1.2.9 Flame Seal® IB (FS-IB) Intumescent Coating:** Flame Seal IB intumescent coating, manufactured by Flame Seal Products, Inc., is a single component, water-based, liquid-applied intumescent coating. The coating is supplied in 5-gallon pails and 55-gallon drums and has a shelf-life of six months when stored in factory-sealed containers at temperatures between 60°F and 80°F.

### 3.2 Performance Characteristics:

**3.2.1 Surface Burning Characteristics:** The insulations have a flame-spread index of 25 or less and a smoke-developed index of 450 or less when tested in accordance with ASTM E84 at a maximum thickness of 4





inches. Based on large-scale tests in accordance with NFPA 286, the insulations can be installed at greater thicknesses as described in Section 4.3 and 4.4. When the insulation is separated from the interior living space of the building with minimum 1/2-inch-thick gypsum board, the maximum insulation thickness of the insulations is not limited. Under the IRC, a thermal barrier of minimum 23/32-inch-thick wood structural panel is also permitted, and the maximum insulation thickness is not limited.

**3.2.2 Thermal Resistance:** The insulations have thermal resistance (*R*-value), at a mean temperature of 75°C, as shown in Table 2.

**3.2.3 Air Permeability:** SPRAYTITE® (SP, 158, and 178) and WALLTITE® US insulations, at a minimum thickness of 1 inch, are considered air-impermeable insulation in accordance with IBC Section 202 and IRC Section R202, based on testing in accordance with ASTM E2178 and/or ASTM E283.

**3.2.4 Air Barrier:** SPRAYTITE® (SP, 158, and 178) and WALLTITE® US insulations, at a minimum thickness of 1 inch, are considered air barrier materials in accordance with IECC Section C402.6.2.3.1.

**3.2.5 Moisture Vapor Permeance:** The insulations have a moisture vapor permeance of less than 1 perm and qualify as Class II vapor retarders, based on testing in accordance with ASTM E96, when applied at the following minimum thicknesses:

SPRAYTITE® (SP and 158) at 1-1/4 inches

SPRAYTITE® 178 at 1-1/2 inches

WALLTITE® US at 1-1/2 inches

## 4.0 INSTALLATION

### 4.1 General:

The insulations must be installed in accordance with the manufacturer's published installation instructions, the applicable Code, and this Research Report. A copy of the manufacturer's instructions must be available on the jobsite during installation.

### 4.2 Application:

The insulations are spray-applied on the jobsite using plural-component metering and processing equipment as recommended in the manufacturer's published installation instructions. All insulations (except SPRAYTITE® SP) are applied in passes having a minimum thickness of 1/2 inch and a maximum thickness of 2 inches per pass, up to the total thickness specified in Sections 3.2, 4.3, and 4.4 of this report. Each insulation pass must be allowed to fully expand, cure, and cool for a minimum of 10 minutes per inch prior to application of a subsequent pass. SPRAYTITE® SP may be applied at thicknesses up to 4 inches maximum per pass, with a cooling time of 10 minutes per inch of thickness between each pass. The insulation must not be used in areas that have a maximum continuous service temperature greater than 180°F or in contact with heat-producing appliances. The foam plastic insulations must not be used in electrical outlet or junction boxes. The substrate must be free of moisture, frost or ice, loose scales, rust, oil, and grease, or other surface contaminants. The insulations must be protected from the weather during and after application, except for applications in accordance with Section 4.5.

### 4.3 Thermal Barrier:

**4.3.1 Application with a Prescriptive Thermal Barrier:** The insulations must be separated from the interior of the building by a prescriptive thermal barrier of minimum 1/2-inch gypsum wallboard or an approved equivalent 15-minute thermal barrier complying with, and installed in accordance with, IBC Section 2603.4 or IRC Section R303.4, as applicable. Exceptions are provided in Section 4.3.2 and Section 4.4, or when the installation is in sill plates and headers at a total thickness of 3-1/4 inches or less as permitted by IRC Section R303.5.11.

When the insulations are separated from the interior living space of the building with minimum 1/2-inch-thick gypsum board, the maximum insulation thickness of the insulations is not limited. Under the IRC, a thermal barrier of minimum 23/32-inch-thick wood structural panel is also permitted, and the maximum insulation thickness is not limited.





**4.3.2 Application without a Prescriptive Thermal Barrier:** The SPRAYTITE® (SP, 158, and 178) and WALLTITE® US insulations may be installed without the 15-minute thermal barrier prescribed in IBC Section 2603.4 and IRC Section R303.4, in assemblies conforming to one of the assemblies described in Table 3. The insulation and coating may be left exposed as an interior finish as indicated in Table 3.

#### 4.4 Attics and Crawl Spaces:

**4.4.1 Application with a Prescriptive Ignition Barrier:** When the insulations are installed within attics or crawl spaces where entry is made only for service of utilities, an ignition barrier must be installed in accordance with IBC Section 2603.4.1.6 or IRC Sections R303.5.3 and R303.5.4, as applicable. The ignition barrier must be consistent with the requirements for the type of construction required by the applicable Code and must be installed in a manner so that the foam plastic insulation is not exposed.

**4.4.2 Application without a Prescriptive Ignition Barrier:** The SPRAYTITE® (SP, 158, and 178) and WALLTITE® US insulations may be installed in attics and crawl spaces as described in this section and Table 4, without the ignition barriers described in IBC Section 2603.4.1.6 and IRC Sections R303.5.3 and R303.5.4, subject to the following conditions:

- a. Entry to the attic or crawl space is to service utilities, and no storage is permitted.
- b. There are no interconnected attic or crawl space areas.
- c. Air in the attic or crawl space is not circulated to other parts of the building.
- d. Attic ventilation is provided when required by IBC Section 1202.2 or IRC Section R806, except when air-impermeable insulation is permitted in unvented attics in accordance with IBC Section 1202.3 or IRC Section R806.5. Under-floor (crawl space) ventilation is provided when required by IBC Section 1202.4 or IRC Section R408.3, as applicable.
- e. Combustion air is provided in accordance with International Mechanical Code (IMC) Section 701.

In attics, the insulation may be spray-applied to the underside of roof sheathing or roof rafters, and/or vertical surfaces provided the assembly conforms to one of the assemblies described in Table 4. In crawl spaces,

the insulations may be spray-applied to the underside of floors and/or vertical surfaces provided the assembly conforms to one of the assemblies described in Table 4. When an intumescent coating is used, surfaces to be coated must be dry, clean, and free of dirt, loose debris, and any other substances that could interfere with adhesion of the coating. The intumescent coating must be applied to all surfaces in accordance with the respective coating manufacturer's installation instructions. The coating must be applied when ambient and substrate temperatures are above 50°F unless otherwise permitted by the intumescent coating manufacturer's installation instructions. The insulations may be installed in unvented attics as described in this section in accordance with IBC Section 1202.3 or IRC Section R806.5.

**4.4.3 Use on Attic Floors:** The SPRAYTITE® (SP, 158, and 178) and WALLTITE® US insulations may be installed in accordance with this section and Table 4 between and over the joists in attic floor. The insulation must be separated from the interior of the building by an approved thermal barrier. The ignition barrier required in IBC Section 2603.4.1.6 and IRC Section R303.5.3 may be omitted.

#### 4.5 Water-Resistive Barrier:

SPRAYTITE® 178 and WALLTITE® US insulations may be used as an alternative to the water-resistive barrier prescribed in IBC Section 1403.2 and IRC Section R703.2, when installed on exterior walls as described in this section. The insulation must be spray-applied to the exterior side of the sheathing, masonry, or other suitable exterior wall substrates to form a continuous layer of 1-inch minimum thickness. All construction joints and penetrations must be sealed with SPRAYTITE® 178 or WALLTITE® US insulation. The insulation must be covered with an exterior wall covering within the time specified in the BASF installation instructions.

#### 4.6 Fire-Resistance-Rated Wall Assemblies:

**4.6.1 Two-hour Fire-resistance-rated Wall Assembly (Load Bearing):** SPRAYTITE® (SP or 158) may be installed on interior load-bearing 2-hour fire-resistance-rated walls, when installed in accordance with the following:





**4.6.1.1 Wood Framing:** Two rows on separate plates, 3 inches apart, of minimum 2 × 4 wood studs (No. 2 Douglas fir) spaced a maximum of 16 inches on center.

**4.6.1.2 Wall Finish:** Base layer of 5/8 thick Type X gypsum wallboard applied horizontally and fastened to each outer side of a double row of studs with 6d by 1-7/8-inch-long coated nails, spaced 24 inches on center. Face layer of 5/8 inch thick Type X gypsum board is applied horizontally and fastened to each outer side of studs over the base layer with 8d by 2-3/8-inch-long coated nails, spaced 8 inches on center. Gypsum wallboard joints must be staggered 24 inches between layers and on opposite sides of the wall.

**4.6.1.3 Insulation:** SPRAYTITE® (SP or 158) is applied in the stud cavities of both rows at a thickness of 3 inches.

**4.6.2 Other Fire-resistance-rated Assemblies:** SPRAYTITE® (SP, 158, and 178) and WALLTITE® US insulations have been tested for compliance with UL 263 (ASTM E119). Refer to the UL LLC Fire-resistance Directory at [www.ul.com](http://www.ul.com).

The UL design listings have not been evaluated under this Research Report.

#### 4.7 Exterior Walls in Types I, II, III, and IV Construction:

SPRAYTITE® 178 and WALLTITE® US may be installed in or on exterior walls of buildings of Type I, II, III, and IV construction complying with IBC Section 2603.5 and as described in this section. The maximum thickness of the foam plastic is 3 inches when installed on the exterior of the sheathing and 3-5/8 inches when installed in stud cavities. The potential heat of SPRAYTITE® 178 and WALLTITE® US spray-applied insulations is 1961 Btu/ft<sup>2</sup> per inch of thickness. The tested wall assemblies were extended through a third-party engineering analysis to include additional wall constructions described in Tables 5 through 8.

## 5.0 CONDITIONS OF USE

The BASF Corporation spray-applied polyurethane foam insulations described in this Research Report comply with, or are a suitable alternative to, what is specified in those Codes listed in Section 1.0 of this report, subject to the following conditions:

**5.1** Installation must comply with this Research Report, the applicable Code, and the report holder's published installation instructions. In the event of a conflict between the manufacturer's instructions and this report, this report governs.

**5.2** The insulations must be separated from the interior of the building by an approved 15-minute thermal barrier or approved alternate thermal barrier, as described in Section 4.3, except where installation is in an attic or crawl space as described in Section 4.4.

**5.3** The insulations must not exceed the thickness limitations noted in Section 3.2, 4.3, 4.4, 4.5, 4.6 or 4.7, as applicable.

**5.4** The insulations must be applied by professional spray polyurethane foam installers approved by BASF Corporation or approved by the Spray Polyurethane Foam Alliance (SPFA) for the installation of spray polyurethane foam insulation.

**5.5** Use of the insulations in areas where the probability of termite infestation is "very high" must be in accordance with IBC Section 2603.8 or IRC Section R305.4, as applicable.

**5.6** Jobsite certification and labeling of the insulation must comply with IRC Section N1101.10, N1101.14 and IECC Section C303.1, or R303.1 and R401.3, as applicable.

**5.7** The polyurethane foam plastic insulation components are produced under a quality control program with inspections by Intertek Testing Services NA, Inc.

## 6.0 SUPPORTING EVIDENCE

**6.1** Reports of tests in accordance with ASTM C518, ASTM E84, ASTM E96, ASTM E119, ASTM E283, ASTM E2178, NFPA 259, NFPA 285, NFPA 286, UL 263, and UL 1715.

**6.2** Data in accordance with the ICC-ES Acceptance Criteria for Spray-applied Foam Plastic Insulation (AC377), dated February 2020, including reports of tests in accordance with Appendix X.





6.3 Data in accordance with ICC 1100 (2019).

6.4 Research Reports for evaluation of data in accordance with ICC-ES Acceptance Criteria for Fire-protective Coatings Applied to Spray-applied Foam Plastic Insulation Installed without a Code-prescribed Thermal Barrier (AC456), dated October 2015.

6.5 Intertek Listing Report: ["BASF SPRAYTITE and WALLTITE Spray-applied Polyurethane Foam Insulation \(HFC\)"](#)

6.6 Hughes Associates, Inc., letters dated April 18, 2011; April 14, 2014; and October 7, 2014, Re. HAI Project 1JJB00019.001; and dated March 23, 2010, Re. HAI Project 1JJB00019000.

**7.0 IDENTIFICATION**

The A and B components of the insulation are identified with the BASF Corporation name and address, the product name, the product type (A or B component), density, the flame-spread and smoke-developed indices, the shelf life, the manufacturing location, the date of manufacture, the Intertek Mark as shown below, and the Code Compliance Research Report number (CCRR-1031). Intumescent coatings are identified with the manufacturer’s name, the product trade name, use instructions and the applicable Evaluation Report number.



**8.0 OTHER CODES**

This section is not applicable.

**9.0 CODE COMPLIANCE RESEARCH REPORT USE**

9.1 Approval of building products and/or materials can only be granted by a building official having legal authority in the specific jurisdiction where approval is sought.

9.2 Code Compliance Research Reports shall not be used in any manner that implies an endorsement of the product by Intertek.

9.3 Reference to the <https://bpdirectory.intertek.com> is recommended to ascertain the current version and status of this report.

This Code Compliance Research Report (“Report”) is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this Report. Only the Client is authorized to permit copying or distribution of this Report and then only in its entirety, and the Client shall not use the Report in a misleading manner. Client further agrees and understands that reliance upon the Report is limited to the representations made therein. The Report is not an endorsement or recommendation for use of the subject and/or product described herein. This Report is not the Intertek Listing Report covering the subject product and utilized for Intertek Certification and this Report does not represent authorization for the use of any Intertek certification marks. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek.





TABLE 1 – PROPERTIES EVALUATED

| PROPERTY  | 2024 IBC SECTION <sup>1</sup> | 2024 IRC SECTION <sup>1</sup> | 2024 IECC SECTION <sup>1</sup> |
|---|-------------------------------|-------------------------------|--------------------------------|
| Physical properties                             | 2603.1.1                      | Not required                  | Not required                   |
| Surface-burning characteristics                 | 2603.3                        | R303.3                        | Not applicable                 |
| Alternative to thermal barrier/ignition barrier | 2603.4                        | R303.4                        | Not applicable                 |
| Air permeability                                | 1202.3                        | R806.5                        | C402.5<br>R402.4               |
| Vapor permeance                                 | 202, 1404.3                   | 202, R702.7                   | Not applicable                 |
| Alternative to water-resistive barrier          | 1403.2                        | R703.2                        | Not applicable                 |
| Fire-resistance-rated construction              | 703                           | R302                          | Not applicable                 |
| Exterior walls in Types I-IV construction       | 2603.5                        | Not applicable                | Not applicable                 |
| Thermal resistance                              | 1301                          | N1101.10<br>N1102             | C303.1<br>R303.1               |

<sup>1</sup> Section numbers may be different for earlier editions of the International Codes.



TABLE 2 – THERMAL RESISTANCE OF SPRAYTITE® (SP, 158, and 178) AND WALLTITE® US INSULATIONS

| SPRAYTITE® (SP and 158)         |   |
|---------------------------------|---|
| THICKNESS (INCHES)              | R-VALUE <sup>1</sup> (°F.ft <sup>2</sup> .h/Btu) <sup>1</sup> |
| 1                               | 6.6   |
| 2                               | 13  |
| 3                               | 20  |
| 3.5                             | 24  |
| 4                               | 27  |
| 5                               | 34  |
| 6                               | 41  |
| 7                               | 48  |
| 8                               | 54  |
| 10                              | 68  |
| 11                              | 75  |
| 12                              | 82  |
| SPRAYTITE® 178 and WALLTITE® US |   |
| 1                               | 6.7   |
| 2                               | 13  |
| 3                               | 20  |
| 3.5                             | 24  |
| 4                               | 28  |
| 5                               | 34  |
| 6                               | 41  |
| 7                               | 48  |
| 8                               | 55  |
| 10                              | 69  |
| 11                              | 76  |
| 12                              | 83  |

<sup>1</sup>R-values are calculated based on tested K values at 1- and 3.5-inch thicknesses. R-values greater than 3.5 inches are calculated using R = 6.86 / inch.  
R-values greater than 10 are rounded to the nearest whole number.



TABLE 3 – USE OF INSULATION WITHOUT A PRESCRIPTIVE THERMAL BARRIER

| INSULATION TYPE                      | MAXIMUM THICKNESS (in) (Wall Cavities) | MAXIMUM THICKNESS (in) (Ceilings, Underside of Roof Sheathing / Rafters & Floors) | INTUMESCENT COATING MINIMUM THICKNESS & TYPE (Applied to all Foam Surfaces) | MINIMUM APPLICATION RATE OF THE INTUMESCENT COATING | May be left exposed as an Interior Finish | TESTS SUBMITTED (AC377) |
|--------------------------------------|--|---|---|---|---|-------------------------|
| WALLTITE®<br>US<br>SPRAYTITE®<br>178 | 6                                      | 8   | No-Burn Plus ThB<br>17 wet mils   | 1.06 gal / 100 ft <sup>2</sup>                      | Yes                                       | UL 1715                 |
|                                      | 5-1/2                                  | 11-1/2  | 4 wet mils DC315<br>Primer<br>16 wet mils DC315                             | 1.00 gal / 100 ft <sup>2</sup>                      | Yes                                       | NFPA 286                |
|                                      | 5-1/2                                  | 7-1/2   | Fireshell F10E<br>23 wet mils   | 1.23 gal / 100 ft <sup>2</sup>                      | Yes                                       | NFPA 286                |
| SPRAYTITE®<br>(SP, 158)              | 6                                      | 8   | No-Burn Plus ThB<br>14 wet mils   | 0.87 gal / 100 ft <sup>2</sup>                      | Yes                                       | UL 1715                 |
|                                      | 5-1/2                                  | 9-1/2   | DC315<br>14 wet mils  | 0.88 gal / 100 ft <sup>2</sup>                      | Yes                                       | NFPA 286                |
|                                      | 5-1/2                                  | 9-1/2   | Fireshell F10E<br>21 wet mils   | 1.16 gal / 100 ft <sup>2</sup>                      | Yes                                       | NFPA 286                |



TABLE 4 – USE OF INSULATION IN ATTICS AND CRAWL SPACES WITHOUT A PRESCRIPTIVE IGNITION BARRIER

| INSULATION TYPE                      | MAXIMUM THICKNESS (in)<br>(Wall Cavities & Attic Floors) | MAXIMUM THICKNESS (in)<br>(Underside of Roof Sheathing/Rafters & Floors) | INTUMESCENT COATING MINIMUM THICKNESS & TYPE (Applied to all Foam Surfaces) | MINIMUM APPLICATION RATE OF THE INTUMESCENT COATING | TESTS SUBMITTED (AC377) |
|--------------------------------------|--|--|---|---|-------------------------|
| WALLTITE®<br>US<br>SPRAYTITE®<br>178 | 9-1/4  | 11-1/4   | No coating required   | NA  | Appendix X              |
|                                      | 9-1/4  | 11-1/4   | Fireshell IB-4<br>10 wet mils   | 0.60 gal / 100 ft <sup>2</sup>                      | Appendix X              |
|                                      | 9-1/4  | 11-1/4   | ALDOCOAT 800<br>18 wet mils   | 1.12 gal / 100 ft <sup>2</sup>                      | Appendix X              |
|                                      | 9-1/4  | 11-1/4   | NoBurn Plus<br>12 wet mils  | 0.75 gal / 100 ft <sup>2</sup>                      | Appendix X              |
|                                      | 8  | 12   | Flame Seal TB<br>25 wet mils  | 1.60 gal / 100 ft <sup>2</sup>                      | UL 1715                 |
|                                      | 8  | 12   | DC315<br>20 wet mils  | 1.25 gal / 100 ft <sup>2</sup>                      | Appendix X              |
|                                      | 5-1/2  | 11-1/2   | DC315<br>4 wet mils   | 0.25 gal / 100 ft <sup>2</sup>                      | Appendix X              |
| SPRAYTITE®<br>(SP, 158)              | 7-1/4  | 11-1/4   | No coating required   | NA  | Appendix X              |
|                                      | 5-1/2  | 9-1/2  | Fireshell F10E<br>21 wet mils   | 1.16 gal / 100ft <sup>2</sup>                       | NFPA 286                |
|                                      | 8  | 8  | No-Burn Plus XD<br>6 wet mils   | 0.31 gal / 100ft <sup>2</sup>                       | Appendix X              |
|                                      | 11-1/4   | 11-1/4   | Flame Seal TB<br>24 wet mils  | 1.60 gal / 100ft <sup>2</sup>                       | UL 1715                 |
|                                      | 11-1/2   | 11-1/2   | Flame Seal FS-IB<br>8 wet mils  | 0.50 gal / 100ft <sup>2</sup>                       | Appendix X              |
|                                      | 5-1/2  | 9-1/2  | DC315<br>14 wet mils  | 0.88 gal / 100ft <sup>2</sup>                       | NFPA 286                |
|                                      | 5-1/2  | 11-1/2   | DC315<br>4 wet mils   | 0.25 gal / 100 ft <sup>2</sup>                      | Appendix X              |

NA = not applicable.





TABLE 5 – NFPA 285 COMPLYING WALLS – SPRAYTITE® 178 OR WALLTITE US ON EXTERIOR

| Wall Component   | Materials   |
|--|---|
| Base Wall System – Use either 1, 2, or 3   | <ul style="list-style-type: none"> <li>1 – Concrete wall</li> <li>2 – Concrete Masonry wall</li> <li>3 – 1-layer of 5/8-inch-thick Type X gypsum wallboard installed on the interior side of minimum 3-5/8-inch-deep minimum 20-gauge thick steel studs spaced a maximum of 24 inch on center. Lateral bracing installed minimum every 4 ft. vertically or as required. Wall stud cavities shall be filled at each floor line with minimum 4 lbs/ft<sup>3</sup> mineral wool (e.g., Thermafiber) friction fit between steel wall studs</li> </ul>   |
| Perimeter Fire Barrier System  | Perimeter fire barrier system complying with IBC Section 715.4 shall be installed, as applicable, to fill the void between the edge of the concrete floor slab and the interior surface of the exterior wall  |
| Interior Insulation – Use either 1, 2, 3, 4, or 5; or combination of 2 and 4 or combination of 2 and 5.                                    | <ul style="list-style-type: none"> <li>1 – None</li> <li>2 – Maximum 6-inch thickness of ENERTITE® Max or ENERTITE® G (CCRR-1032) applied to interior surface of Base Wall System 1 and 2 (See Note 1)</li> <li>3 – Full wall stud cavity depth or less of ENERTITE® Max or ENERTITE® G applied using exterior gypsum sheathing of Base Wall System 3 as the substrate and covering the width of the cavity and the inside of the steel wall stud framing flange.</li> <li>4 – Fiberglass batt insulation (faced or unfaced)</li> <li>5 – Mineral wool insulation (faced or unfaced)</li> </ul>   |
| Exterior Sheathing – Use either 1, 2, or 3. If wall stud cavity insulation is ENERTITE® NM or ENERTITE® G SPF (CCRR-1032), then use 3 only | <ul style="list-style-type: none"> <li>1 – None (for Base Wall Systems 1 or 2)</li> <li>2 – 1/2-inch-thick exterior type gypsum sheathing (for Base Wall System 3)</li> <li>3 – 5/8-inch-thick Type X exterior type gypsum sheathing (for Base Wall System 3)</li> </ul>  |
| Exterior Insulation  | Maximum 3-inch thickness of SPRAYTITE® 178 or WALLTITE® US  |
| (Optional) Exterior Insulation Covering – Use 1 or 2   | <ul style="list-style-type: none"> <li>1 – None</li> <li>2 – As an option, cover SPRAYTITE® 178 or WALLTITE® US with minimum 2-inch thickness of minimum 4 pcf mineral wool insulation. Mineral wool insulation installation shall be in accordance with Table 8 requirements.</li> </ul>   |
| Exterior Wall Covering – Use either 1, 2, 3, 4, or 5   | <ul style="list-style-type: none"> <li>1 – Brick – Standard type brick veneer anchors, installed a maximum 24 inches on center, vertically on each stud with maximum 2-inch air gap between exterior insulation and brick. Brick to be standard nominal 4-inch-thick clay brick installed in a running bond pattern using Type S mortar.</li> <li>2 – Stucco – Minimum 3/4-inch thick, exterior cement plaster and lath. A secondary water-resistive barrier can be installed between the exterior insulation and the lath. The secondary water-resistive barrier shall not be full-coverage asphalt or butyl-based self-adhered membranes.</li> <li>3 – Minimum 2-inch-thick natural stone (granite, limestone, marble, sandstone). Any standard non-open jointed installation technique can be used.</li> <li>4 – Minimum 1-1/2-inch-thick concrete masonry unit (CMU), pre-cast concrete, or artificial cast stone. Any standard non-open jointed installation technique can be used.</li> <li>5 – Minimum 1-1/4-inch-thick Terra Cotta non-open jointed. Any standard non-open jointed installation technique can be used.</li> </ul> |
| Flashing of window, door and other exterior wall penetrations.   | As an option, flash around window, door, and other exterior penetrations with limited amounts of maximum 12-inch-wide flashing tape (acrylic, asphalt or butyl-based) or liquid-applied membrane material with or without fiber mesh reinforcement.   |

**Note 1:** Fireblocking per IBC Section 718 and thermal barrier material requirements must be met for Base Wall Systems 1 and 2, as required by specific wall construction details when combustible concealed space is created on interior side of exterior wall assembly.

**Note 2:** Building Code section references may change in different editions of the IBC.





TABLE 6 – NFPA 285 WALLS – SPRAYTITE® 178 OR WALLTITE® US ON EXTERIOR WITH EXTERIOR INSULATION COVERING

| Wall Component   | Materials   |
|--|---|
| Base Wall System – Use either 1, 2, or 3   | <ol style="list-style-type: none"> <li>1 – Concrete wall</li> <li>2 – Concrete Masonry wall</li> <li>3 – 1 layer of 5/8-inch-thick Type X gypsum wallboard installed on the interior side of minimum 3-5/8-inch-deep minimum 20 gauge thick steel studs spaced a maximum of 24 inches on center. Lateral bracing installed minimum every 4 ft. vertically or as required. Wall stud cavities shall be filled at each floor line with minimum 4 lb/ft<sup>3</sup> mineral wool (e.g. Thermafiber) friction fit between steel wall studs</li> </ol>   |
| Perimeter Fire Barrier System  | Perimeter fire barrier system complying with IBC Section 715.4 shall be installed, as applicable, to fill the void between the edge of the concrete floor slab and the interior surface of the exterior wall assembly.  |
| Interior Insulation – Use either 1, 2, 3, 4, or 5; or combination of 2 and 4 or combination of 2 and 5                                     | <ol style="list-style-type: none"> <li>1 – None</li> <li>2 – Maximum 6-inch-thickness of ENERTITE® Max or ENERTITE® G (CCRR-1032) applied to interior surface of Base Wall System 1 and 2 (See Note 1)</li> <li>3 – Full wall stud cavity depth or less of ENERTITE® Max or ENERTITE® G applied using exterior gypsum sheathing of Base Wall System 3 as the substrate and covering the width of the cavity and the inside of the steel wall stud framing flange.</li> <li>4 – Fiberglass batt insulation (faced or unfaced)</li> <li>5 – Mineral wool insulation (faced or unfaced)</li> </ol> |
| Exterior Sheathing – Use either 1, 2, or 3. If wall stud cavity insulation is ENERTITE® NM or ENERTITE® G SPF (CCRR-1032), then use 3 only | <ol style="list-style-type: none"> <li>1 – None (for Base wall systems 1 or 2)</li> <li>2 – 1/2-inch-thick exterior type gypsum sheathing (for Base Wall System 3)</li> <li>3 – 5/8-inch-thick Type X exterior type gypsum sheathing (for Base Wall System 3)</li> </ol>  |
| Exterior Insulation  | Maximum 3-1/2-inch-thickness of SPRAYTITE® 178 or WALLTITE® US  |
| Exterior Insulation Covering   | Cover SPRAYTITE® 178 or WALLTITE® US with minimum 2-inch thickness of minimum 4 pcf mineral wool insulation. Mineral wool insulation installation shall be in accordance with Table 8 requirements.   |
| Exterior Wall Covering – Use either 1, 2, or 3 (See Note 3)  | <ol style="list-style-type: none"> <li>1 – Any non-combustible exterior wall covering material using any standard installation technique</li> <li>2 – Any non-combustible exterior wall covering system with a combustible WRB that has successfully been tested in accordance with NFPA 285.</li> <li>3 – Any combustible exterior wall covering system with or without a combustible WRB that has successfully been tested in accordance with NFPA 285</li> </ol>   |
| Flashing of window, door and other exterior wall penetrations.   | As an option, flash around window, door, and other exterior penetrations with limited amounts of maximum 12-inch-wide flashing tape (acrylic, asphalt or butyl-based) or liquid applied membrane material with or without fiber mesh reinforcement.   |

**Note 1:** Fireblocking per IBC Section 718 and thermal barrier material requirements must be met for Base Wall Systems 1 and 2, as required by specific wall construction details when combustible concealed space is created on interior side of exterior wall assembly.

**Note 2:** Building Code section references may change in different editions of the IBC.

**Note 3:** Combustible exterior wall coverings shall be installed in accordance with manufacturer's installation requirements.





TABLE 7 – NFPA 285 COMPLYING WALLS – SPRAYTITE® 178 OR WALLTITE® US IN INTERIOR WALL CAVITY

| Wall Component   | Materials   |
|--|---|
| Base Wall System – Use either 1, 2, or 3   | 1 – Concrete wall<br>2 – Concrete Masonry wall<br>3 – 1 layer of 5/8-inch-thick Type X gypsum wallboard installed on the interior side of minimum 3-5/8-inch-deep minimum 20 gauge thick steel studs spaced a maximum of 24 inch on center. Lateral bracing installed minimum every 4 feet vertically or as required. Wall stud cavities shall be filled at each floor line with minimum 4 lb/ft <sup>3</sup> mineral wool (e.g., Thermafiber) friction fit between steel wall studs.                             |
| Perimeter Fire Barrier System  | Perimeter fire barrier system complying with IBC Section 715.4 shall be installed, as applicable, to fill the linear gap between the edge of the concrete floor slab and the interior surface of the exterior wall assembly.  |
| Interior Insulation – Use either 1, 2, 3, 4 or 5 or combinations of 3 with 4 or 3 with 5 | 1 – None<br>2 – Maximum 3-5/8-inch-thickness of SPRAYTITE® 178 or WALLTITE® US applied to interior surface of Base Wall System 1 and 2 (See Note 1)<br>3 – Full wall stud cavity depth or less of SPRAYTITE® 178 or WALLTITE® US applied using exterior gypsum sheathing of Base Wall System 3 as the substrate and covering the width of the cavity and the inside of the steel wall stud framing flange.<br>4 – Fiberglass batt insulation (faced or unfaced)<br>5 – Mineral wool insulation (faced or unfaced) |
| Exterior Sheathing   | 5/8-inch-thick Type X exterior type gypsum sheathing (for Base Wall System 3)   |
| Exterior Wall Covering   | Any non-combustible exterior wall covering material using any standard installation technique   |
| Flashing of window, door and other exterior wall penetrations.                           | As an option, flash around window, door, and other exterior penetrations with limited amounts of maximum 12-inch-wide flashing tape (acrylic, asphalt or butyl-based) or liquid applied membrane material with or without fiber mesh reinforcement.   |

**Note 1:** Fireblocking per IBC Section 718 and thermal barrier material requirements must be met for Base Wall Systems 1 and 2, as required by specific wall construction details when combustible concealed space is created on interior side of exterior wall assembly.

**Note 2:** Building Code section references may change in different editions of the IBC.





TABLE 8 – MINERAL WOOL INSULATION INSTALLATION REQUIREMENTS FOR TABLES 5 AND 6

| Wall Component                                    | Requirements  |
|---|---|
| Mineral Wool Insulation Installation Requirements | <ol style="list-style-type: none"> <li>1 – Mineral wool insulation shall be mechanically fastened to the wall surface using perforated base insulation pins.</li> <li>2 – Each insulation pin shall be screwed into exterior sheathing and/or steel wall studs.</li> <li>3 – The length of the insulation pin shall be sized to accommodate the thickness of the SPF plus the mineral wool insulation thickness plus a minimum of 1 inch.</li> <li>4 – Insulation pin spacing shall be such that a pin is located in each corner of each mineral wool batt as well as one pin located in the geometric center of each insulation batt.</li> <li>5 – All pins shall be located nominally 2 inches in from the edge of the insulation batt.</li> <li>6 – SPF shall be installed onto the exterior wall surface such that the perforated pin bases are fully encapsulated.</li> <li>7 – Mineral wool insulation shall be impaled onto the insulation pins and secured using nominal 2-1/2- inch square galvanized speed friction washers.</li> <li>8 – Insulation pin tips protruding beyond the speed friction washer shall be bent over to prevent the washer from falling off.</li> <li>9 – Mineral wool batts shall be tightly fitted against adjacent batts and joints shall be staggered a minimum of one-half batt insulation width (minimum 12 inches).</li> </ol> |
| Mineral Wool Specifications                       | <ol style="list-style-type: none"> <li>1 – Mineral wool insulation shall meet the requirements of ASTM C612.</li> <li>2 – Mineral wool insulation shall not have any type of facer (foil, etc.) on either side.</li> <li>3 – Mineral wool insulation shall be noncombustible when tested in accordance with ASTM E136.</li> <li>4 – The mineral wool insulation density shall be a minimum of 4.0 lbs/ft<sup>3</sup>.</li> <li>5 – The R-value per inch for the mineral wool insulation shall be a minimum of 3.45</li> <li>6 – Mineral wool insulation shall be installed as described above.</li> </ol>   |